

EchoPanel® 12mm

Designer: Woven Image

Application(s): Walls, Workstations, Partitions, Ceilings

Composition & Pattern

Composition 100% PET (60% post-consumer recycled)

Colours Available 35

Dimensions & Weight

Dimensions Length: 2800mm (+/- 10mm), Width: 1200mm (+/- 5mm),
Thickness: 12mm (+/- 7%)

Unit of Sale Panel

Unit of Sale Net Weight (kg) 8

Performance

Fire Test Result AS 1530.3, BS EN 13501.1: Classification B - s1, d0, ISO 9705: Group 1, BS EN 45545-2 + A1 Annex C: CIT: 0.05, ASTM E84 Unadhered: Class 1 or A

Acoustic Performance Standard Test Method AS ISO 354: 2006 (R2016), AS ISO 11654: 2002 (2016), ASTM C423 - 17

Noise Reduction Coefficient (NRC) Result Direct fix: 0.45, 20mm air gap: 0.60, 50mm air gap: 0.75

Sound Absorption Average (SAA) Result	Direct fix: 0.43, 20mm air gap: 0.61, 50mm air gap: 0.75
Weighted Sound Absorption Coefficient (αw) Result	Direct fix: 0.30 (MH), 20mm air gap: 0.45 (MH), 50mm air gap: 0.60 (MH)
Sound Absorption Class	D (Direct fix), D (20mm air gap), C (50mm air gap)
Additional Acoustic Information	Noise reduction coefficient result key: H = High Frequency & MH = Mid to High Frequency
Colour Fastness to Light Standard Test Method	ISO 105 B02
Colour Fastness Light Rating	6 - 7
Flexural Properties Standard Test Method	ISO 1209 - 1: 2007 @20mm Deflection
Flexural Properties Rating	Direction 1 = 37.3 N, Direction 2 = 39.1 N

Sustainability

VOC Emissions Results ASTM D5116: TVOC Emissions Rate: <0.02mg/m²/hr (7 days), and CDPH Standard Method v1.2: TVOC Emissions Rate: <0.054mg/m³; Formaldehyde Emissions Rate: <2µg/m³

Sustainability Performance



Instructions

Additional Information See Woven Image EchoPanel® Care & Cleaning Guide.
See Woven Image EchoPanel® Installation Guide.

Exact colour matching cannot be guaranteed between batches.
Fibre mix and web variation are natural characteristics of this product.